

















**CARATTERISTICHE TECNICHE**

Technical specifications | Technische Eigenschaften | Caractéristiques techniques  
 Características técnicas | Технические характеристики | 技术特征

**STANDARD EN 14411 - G**

|   | <b>CARATTERISTICHE TECNICHE</b><br>TECHNICAL DATA<br>TECHNISCHE DATEN<br>CARACTERISTIQUES TECHNIQUES<br>CARACTERÍSTICAS TÉCNICAS<br>ТЕХНИЧЕСКИЕ ХАРАКТЕРИСТИКИ<br>技术特征  | <b>NORMA</b><br>STANDARD<br>NORM<br>NORME<br>NORMA<br>НОРМА<br>ЗНАЧЕНИЯ<br>标准 | <b>VALORI PRESCRITTI DALLE NORME EN 14411 - G</b><br>INTERNATIONAL STANDARDS EN 14411 - G<br>INTERNATIONALE NORMWERTE EN 14411 - G<br>VALEURS PREVUES PAR LES NORMES EN 14411 - G<br>VALORES PREVISTOS POR LAS NORMAS EN 14411 - G<br>ПРЕДУСМОТРЕННЫЕ СТАНДАРТОМ EN 14411-G<br>EN 14411 - G标准规定值 | <b>*VALORE MEDIO MIRAGE</b><br>MIRAGE AVERAGE VALUE<br>MIRAGE MITTELWERT<br>VALEURS MOYEN MIRAGE<br>VALOR MEDIO MIRAGE<br>СРЕДНЕЕ ЗНАЧЕНИЕ MIRAGE<br>MIRAGE平均值 |
|---|---|---|--|--|
|   | <b>CARATTERISTICHE DIMENSIONALI - SIZE CHARACTERISTICS - MASSEIGENSCHAFTEN</b><br>DETERMINATION DES CARACTERISTIQUES DIMENSIONNELLES -<br>CARACTERÍSTICAS DIMENSIONALES - РАЗМЕРНЫЕ ХАРАКТЕРИСТИКИ - 尺寸特征   |   |  |  |
|    | <b>LATI</b><br>SIDES - SEITEN<br>COTES - CANTOS<br>РАЗМЕРЫ СТОРОН - 侧边  | EN ISO 10545-2  | ± 0,3% MAX<br>(± 1,0 mm MAX)   | CONFORME<br>COMPLYING  |
|    | <b>SPESSORE</b><br>THICKNESS - DICKE<br>ÉPAISSEUR - ESPESOR<br>ТОЛЩИНА - 厚度   | EN ISO 10545-2  | ± 5,0% MAX<br>(± 0,5 mm MAX)   | CONFORME<br>COMPLYING  |
|    | <b>RETTILINEITÀ DEGLI SPIGOLI</b><br>STRAIGHTNESS OF SIDES - GERADLINIGKEIT DER KANTEN<br>RECTITUDE DES ARETES - RECTITUD DE LOS CANTOS<br>КОСОУГОЛЬНОСТЬ - 边角平直度   | EN ISO 10545-2  | ± 0,3% MAX<br>(± 0,8 mm MAX)   | CONFORME<br>COMPLYING  |
|    | <b>ORTOGONALITÀ</b><br>RECTANGULARITY - RECHTWINKLIGKEIT<br>PERPENDICULARITÉ - ORTOGONALIDAD<br>КРИВИЗНА СТОРОН - 直角度   | EN ISO 10545-2  | ± 0,3% MAX<br>(± 1,5 mm MAX)   | CONFORME<br>COMPLYING  |
|    | <b>PLANARITÀ</b><br>SURFACE FLATNESS - EBENFLÄCHIGKEIT<br>PLANEITE DE SURFACE - PLANEIDAD<br>КРИВИЗНА ЛИЦЕВОЙ ПОВЕРХНОСТИ - 平整度   | EN ISO 10545-2  | ± 0,4% MAX<br>(± 1,8 mm MAX)   | CONFORME<br>COMPLYING  |
|    | <b>ASSORBIMENTO D'ACQUA</b><br>WATER ABSORPTION - WASSERAUFNAHME<br>ABSORPTION D'EAU - ABSORCIÓN DE AGUA<br>ВОДОПОГЛОЩЕНИЕ - 吸水率  | EN ISO 10545-3  | ≤ 0,5%   | ≤ 0,1%   |
|  | <b>RESISTENZA ALLA FLESSIONE</b><br>FLEXION RESISTANCE - BIEGEFESTIGKEIT<br>RESISTANCE A LA FLEXION - RESISTENCIA A LA FLEXIÓN<br>ПРЕДЕЛ ПРОЧНОСТИ ПРИ ИЗГИБЕ - 抗弯强度  | EN ISO 10545-4  | S ≥ 700 N (< 7,5 mm)<br>S ≥ 1.300 N (> 7,5 mm)<br>R ≥ 35 N/mm²   | ≧ 6 mm: S ≥ 1100 N R ≥ 45 N/mm²<br>≧ 9 mm: S ≥ 2.400 N R ≥ 48 N/mm²  |
|  | <b>RESISTENZA ALL'URTO</b><br>IMPACT RESISTANCE - STOSSFESTIGKEIT<br>RESISTANCE AUX CHOCS - RESISTENCIA A LOS GOLPES<br>УДАРНОСТОЙКОСТЬ - 抗冲击强度   | EN ISO 10545-5  | VALORE DICHIARATO<br>DECLARED VALUE  | > 0,80   |
|  | <b>RESISTENZA ALL'ABRASIONE</b><br>ABRASION RESISTANCE - ABRIEBFESTIGKEIT<br>RESISTANCE A L'ABRASION - RESISTENCIA A LA ABRASIÓN<br>СТОЙКОСТЬ К ИСТИРАНИЮ - 耐磨强度  | EN ISO 10545-6  | ≤ 175 mm³  | < 150 mm³  |
|  | <b>COEFFICIENTE DI DILATAZIONE TERMICA LINEARE</b><br>COEFFICIENT OF LINEAR THERMAL-EXPANSION - LINEARER WÄRMEAUDEHNUNGSKOEFFIZIENT<br>COEFFICIENT DE DILATATION THERMIQUE LINEAIRE - COEFICIENTE DE DILATACIÓN TÉRMICA LINEAL<br>КОЭФФИЦИЕНТ ЛИНЕЙНОГО ТЕРМИЧЕСКОГО РАСШИРЕНИЯ - 线性热膨胀系数 | EN ISO 10545-8  | -  | α=6,6x10 <sup>-6</sup> °C <sup>-1</sup>  |
|  | <b>RESISTENZA AGLI SBALZI TERMICI</b><br>RESISTANCE TO THERMAL SHOCKS - BESTÄNDIGKEIT GEGEN TEMPERATURSCHWANKUNGEN<br>RESISTANCE AUX CHOCS THERMIQUES - RESISTENCIA A LOS CHOQUES TÉRMICOS<br>СТОЙКОСТЬ К ПЕРЕПАДАМ ТЕМПЕРАТУРЫ - 耐热突变性   | EN ISO 10545-9  | TEST SUPERATO SECONDO EN ISO 10545-1<br>PASS ACCORDING EN ISO 10545-1  | NESSUN DANNO<br>NO DAMAGE  |
|  | <b>RESISTENZA AL GELO</b><br>FROST RESISTANCE - FROSTBESTÄNDIGKEIT<br>RESISTANCE AU GEL - RESISTENCIA AL HIELO<br>МОРОЗОСТОЙКОСТЬ - 耐冻性   | EN ISO 10545-12   | TEST SUPERATO SECONDO EN ISO 10545-1<br>PASS ACCORDING EN ISO 10545-1  | NESSUN DANNO<br>NO DAMAGE  |
|  | <b>RESISTENZA ALL'ATTACCO CHIMICO</b><br>RESISTANCE TO CHEMICALS - CHEMIKALIENBESTÄNDIGKEIT<br>RESISTANCE A L'ATTACQUE CHIMIQUE - RESISTENCIA QUÍMICA<br>ХИМИЧЕСКАЯ СТОЙКОСТЬ - 耐化学品作用  | EN ISO 10545-13   | UB MIN.  | A LA HA  |
|  | <b>RESISTENZA ALLE MACCHIE</b><br>RESISTANCE TO STAINS - FLECKENBESTÄNDIGKEIT<br>RESISTANCE AUX TACHES - RESISTENCIA A LAS MANCHAS<br>УСТОЙЧИВОСТЬ К ПЯТНООБРАЗОВАНИЮ - 防污性   | EN ISO 10545-14   | VALORE DICHIARATO<br>DECLARED VALUE  | 5  |
|  | <b>CESSIONE DI PIOMBO E CADMIO</b><br>LEAD AND CADMIUM DISCHARGE - ABGABE VON BLEI UND CADMIUM<br>PERTE DE PLOMB ET CADMIUM - CESIÓN DE PLOMO Y CADMIO<br>ВЫДЕЛЕНИЕ СВИНЦА И КАДМИЯ - 铅和镉的排放  | EN ISO 10545-15   | VALORE DICHIARATO<br>DECLARED VALUE  | < AL LIMITE DI RILEVAMENTO<br>< THAN INSTRUMENT LIMIT  |
|  | <b>SCIVOLOSITÀ</b><br>SKID RESISTANCE - RUTSCHWERT<br>GLISSANCE - ADHERENCIA<br>СКОЛЬЗКОСТЬ - 防滑性   |   |  | SP NAT ST  |
|   |   | DM 236/89 BCRA  | > 0,40   | > 0,40 > 0,40 > 0,40   |
|   |   | ANSI A326.3   | Wet and Dry  | ≥ 0,42 ≥ 0,42 ≥ 0,55   |
|   |   | AS 4586   | -  | P2 P3 -  |
|   |   | DIN 51130   | -  | R9 R10 R11   |
|   |   | DIN 51097   | -  | - A+B A+B+C  |
|   |   | UNE 41901   | ≥ CL1  | CL1 CL1 CL1  |
|   |   | BS 7976 sl.96-4S  | Wet and Dry  | - ≥ 0,36 ≥ 0,36  |
|   |   | BS 7976 sl.55-TRL   | Wet and Dry  | - ≥ 0,36 ≥ 0,36  |

Per i certificati specifici, contattare Mirage SpA - For specific certificates, please contact Mirage SpA - Für die speziellen Zertifikate wenden Sie sich bitte an Mirage SpA - Pour les certificats spécifiques, veuillez contacter Mirage SpA  
 Para los certificados específicos, contactar Mirage SpA - Для сертификатов обращайтесь в компанию Mirage SpA - 关于具体的证书, 请联系Mirage Spa公司