

VOCI DI CAPITOLATO SPECIFICATIONS

Fornitura di pavimento in gres porcellanato **Mirage**.

Supply of **Mirage** porcelain stoneware flooring.

CARATTERISTICHE MERCEOLOGICHE E DI PROCESSO PRODUCTS SECTOR AND PROCESS FEATURES

Lastre in Gres Fine Porcellanato Mirage a sezione piena e greificata in tutto lo spessore, composta da impasto finissimo di argille pregiate con aggiunta di feldspati, quarzi e caolini, ottenute mediante pressatura (450 kg/cm² ed oltre) di impasto atomizzato e successivamente sinterizzate ad un temperatura di circa 1250°C.

La completa greificazione delle lastre permette di avere assorbimenti medi dello 0,04%, ben al di sotto di quanto prescritto dalla norma europea ISO 10545-3.

Il prodotto finito risulta quindi **compatto, antigelo, resistente all'urto, agli attacchi chimici e fisici, alla flessione e agli sbalzi termici**.

Slabs of Mirage Fine Porcelain stoneware, solid and vitrified throughout the mass, consisting of a very fine body made of prized clays with the addition of feldspars, quartzes and kaolins, obtained by pressing (450kg/cm² and more) of the atomized body and then sintered at a temperature of about 1250°C.

Complete vitrification of the slabs makes it possible to have average absorption rates of 0.04%, well below the limits prescribed by ISO 10545-3 European standard.

*The finished product is therefore **compact, frost-proof, impact resistant, resistant to chemical and physical attacks, bending thermal shocks**.*

CONFORMITÀ ALLE NORME EN 14411-G COMPLIANCE WITH EN 14411-G STANDARDS

La collezione **Glocal** risponde a **tutti gli standard EN 14411-G**.

The **Glocal** collection complies with **all EN 14411-G standards**.

CERTIFICAZIONI ECOLOGICHE GREEN CERTIFICATIONS

Alla pari con gli sforzi per mantenere i più alti livelli qualitativi ci siamo sempre impegnati affinché i nostri prodotti e gli stabilimenti abbiano il **minor impatto ambientale possibile**.

Dal controllo delle emissioni e del consumo energetico fino al recupero degli scarti industriali, il nostro modo di lavorare è sempre stato fondato su **principi etici profondi e concreti** per la salvaguardia del nostro habitat, per una qualità della vita migliore per noi ma soprattutto per le generazioni a venire.

Ne sono a testimonianza le numerose certificazioni ottenute da Mirage®, tra le quali l'orientamento **LEED compliant** di tutte le collezioni a catalogo e il rispetto della direttiva **IPPC**, che attesta la conformità a rigidi requisiti e l'utilizzo delle migliori tecniche disponibili per i processi industriali.

*As well as constantly improving the quality of our products, we have always actively involved in reducing the **environmental impact** of our products and factories to the **absolute minimum**.*

*From the control of toxic emissions and energy consumption to the recycling of industrial waste, our work has always been based on **concrete ethical principles** in order to protect the world in which we live, to improve the quality of our lives and those of future generations.*

*This effort can be seen in the numerous certifications obtained by Mirage®, such as the **LEED classifications** for all ceramic collections and the compliance with the **IPPC** regulation, a testament to the respect of strict requirements and the use of the best technology available for industrial processes.*

DESCRIZIONE COMMERCIALE DI PRODOTTO COMMERCIAL DESCRIPTION OF THE PRODUCT

AZIENDA COMPANY Mirage granito ceramico SpA

COLLEZIONE COLLECTION Glocal

FORMATI SIZES	300x300x9 NAT NO SQ	600x1200x9 ST SQ	600x600x20 ST SQ
	150x600x9 SP SQ	800x800x9 NAT SQ	800x800x20 ST SQ
	300x600x9 NAT SQ	800x800x9 SP SQ	900x900x20 ST SQ
	300x600x9 SP SQ	1200x1200x9 SP SQ	600x1200x20 ST SQ
	300x600x9 ST SQ	1200x2400x9 SP SQ	1200x1200x20 ST SQ
	600x600x9 NAT SQ	1200x1200x6 NAT SQ	600x600x30 ST SQ
	600x600x9 SP SQ	1200x2780x6 SP SQ	
	600x600x9 ST SQ	1600x1600x6 SP SQ	
	600x1200x9 NAT SQ	1600x3200x6 SP SQ	
	600x1200x9 SP SQ	1620x3240x12 SLK NO SQ	

SUPERFICI SURFACES Naturale *Natural* Spazzolato Strutturato *Structured* Silk

CARATTERISTICHE TECNICHE

Technical specifications | Technische Eigenschaften | Caractéristiques techniques
 Características técnicas | Технические характеристики | 技术特征

STANDARD EN 14411 - G

	CARATTERISTICHE TECNICHE TECHNICAL DATA TECHNISCHE DATEN CARACTERISTIQUES TECHNIQUES CARACTERÍSTICAS TÉCNICAS ТЕХНИЧЕСКИЕ ХАРАКТЕРИСТИКИ 技术特征	NORMA STANDARD NORM NORME NORMA НОРМА ЗНАЧЕНИЯ 标准	VALORI PRESCRITTI DALLE NORME EN 14411 - G INTERNATIONAL STANDARDS EN 14411 - G INTERNATIONALE NORMWERTE EN 14411 - G VALEURS PREVUES PAR LES NORMES EN 14411 - G VALORES PREVISTOS POR LAS NORMAS EN 14411 - G ПРЕДУСМОТРЕННЫЕ СТАНДАРТОМ EN 14411-G EN 14411 - G标准规定值	*VALORE MEDIO MIRAGE MIRAGE AVERAGE VALUE MIRAGE MITTELWERT VALEURS MOYEN MIRAGE VALOR MEDIO MIRAGE СРЕДНЕЕ ЗНАЧЕНИЕ MIRAGE MIRAGE平均值		
	CARATTERISTICHE DIMENSIONALI - SIZE CHARACTERISTICS - MASSEIGENSCHAFTEN DETERMINATION DES CARACTERISTIQUES DIMENSIONNELLES - CARACTERÍSTICAS DIMENSIONALES - РАЗМЕРНЫЕ ХАРАКТЕРИСТИКИ - 尺寸特征					
	LATI SIDES - SEITEN COTES - CANTOS РАЗМЕРЫ СТОРОН - 侧边	EN ISO 10545-2	± 0,3% MAX (± 1,0 mm MAX)	CONFORME COMPLYING		
	SPESSORE THICKNESS - DICKE EPAISSEUR - ESPESOR ТОЛЩИНА - 厚度	EN ISO 10545-2	± 5,0% MAX (± 0,5 mm MAX)	CONFORME COMPLYING		
	RETTILINEITÀ DEGLI SPIGOLI STRAIGHTNESS OF SIDES - GERADLINIGKEIT DER KANTEN RECTITUDE DES ARETES - RECTITUD DE LOS CANTOS КОСОУГОЛЬНОСТЬ - 边角平直度	EN ISO 10545-2	± 0,3% MAX (± 0,8 mm MAX)	CONFORME COMPLYING		
	ORTOGONALITÀ RECTANGULARITY - RECHTWINKLIGKEIT PERPENDICULARITÉ - ORTOGONALIDAD КРИВИЗНА СТОРОН - 直角度	EN ISO 10545-2	± 0,3% MAX (± 1,5 mm MAX)	CONFORME COMPLYING		
	PLANARITÀ SURFACE FLATNESS - EBENFLÄCHIGKEIT PLANEITE DE SURFACE - PLANEIDAD КРИВИЗНА ЛИЦЕВОЙ ПОВЕРХНОСТИ - 平整度	EN ISO 10545-2	± 0,4% MAX (± 1,8 mm MAX)	CONFORME COMPLYING		
	ASSORBIMENTO D'ACQUA WATER ABSORPTION - WASSERAUFNAHME ABSORPTION D'EAU - ABSORCIÓN DE AGUA ВОДОПОГЛОЩЕНИЕ - 吸水率	EN ISO 10545-3	≤ 0,5%	≤ 0,1%		
	RESISTENZA ALLA FLESSIONE FLEXION RESISTANCE - BIEGEFESTIGKEIT RESISTANCE A LA FLEXION - RESISTENCIA A LA FLEXIÓN ПРЕДЕЛ ПРОЧНОСТИ ПРИ ИЗГИБЕ - 抗弯强度	EN ISO 10545-4	S ≥ 700 N (< 7,5 mm) S ≥ 1.300 N (> 7,5 mm) R ≥ 35 N/mm ² .	≠6 mm: S≥1100N R≥45 N/mm ² ≠9 mm: S≥2.400N R≥48 N/mm ² ≠12 mm: S≥4.000N R≥48 N/mm ² ≠20 mm: S≥12.500N R≥48 N/mm ² ≠30 mm: S≥26.000N R≥48 N/mm ²		
	RESISTENZA ALL'URTO IMPACT RESISTANCE - STOSSFESTIGKEIT RESISTANCE AUX CHOCS - RESISTENCIA A LOS GOLPES УДАРООСТОЙКОСТЬ - 抗冲击强度	EN ISO 10545-5	VALORE DICHIARATO DECLARED VALUE	> 0,80		
	RESISTENZA ALL'ABRASIONE ABRASION RESISTANCE - ABRIEBFESTIGKEIT RESISTANCE A L'ABRASION - RESISTENCIA A LA ABRASIÓN СТОЙКОСТЬ К ИСТИРАНИЮ - 耐磨强度	EN ISO 10545-6	≤ 175 mm ³	< 150 mm ³		
	COEFFICIENTE DI DILATAZIONE TERMICA LINEARE COEFFICIENT OF LINEAR THERMAL-EXPANSION - LINEARER WÄRMEAUDEHNUNGSKOEFFIZIENT COEFFICIENT DE DILATATION THERMIQUE LINEAIRE - COEFICIENTE DE DILATACIÓN TÉRMICA LINEAL КОЭФФИЦИЕНТ ЛИНЕЙНОГО ТЕРМИЧЕСКОГО РАСШИРЕНИЯ - 线性热膨胀系数	EN ISO 10545-8	—	α=6,6x10 ⁻⁶ °C ⁻¹		
	RESISTENZA AGLI SBALZI TERMICI RESISTANCE TO THERMAL SHOCKS - BESTÄNDIGKEIT GEGEN TEMPERATURSCHWANKUNGEN RESISTANCE AUX CHOCs THERMIQUES - RESISTENCIA A LOS CHOQUES TÉRMICOS СТОЙКОСТЬ К ПЕРЕПАДАМ ТЕМПЕРАТУРЫ - 耐热突变性	EN ISO 10545-9	TEST SUPERATO SECONDO EN ISO 10545-1 PASS ACCORDING EN ISO 10545-1	NESSUN DANNO NO DAMAGE		
	RESISTENZA AL GELO FROST RESISTANCE - FROSTBESTÄNDIGKEIT RESISTANCE AU GEL - RESISTENCIA AL HIELO МОРОЗОСТОЙКОСТЬ - 耐冻性	EN ISO 10545-12	TEST SUPERATO SECONDO EN ISO 10545-1 PASS ACCORDING EN ISO 10545-1	NESSUN DANNO NO DAMAGE		
	RESISTENZA ALL'ATTACCO CHIMICO RESISTANCE TO CHEMICALS - CHEMIKALIENBESTÄNDIGKEIT RESISTANCE A L'ATTACHE CHIMIQUE - RESISTENCIA QUÍMICA ХИМИЧЕСКАЯ СТОЙКОСТЬ - 耐化学作用	EN ISO 10545-13	UB MIN.	A LA HA		
	RESISTENZA ALLE MACCHIE RESISTANCE TO STAINS - FLECKENBESTÄNDIGKEIT RESISTANCE AUX TACHES - RESISTENCIA A LAS MANCHAS УСТОЙЧИВОСТЬ К ПЯТНООБРАЗОВАНИЮ - 防污性	EN ISO 10545-14	VALORE DICHIARATO DECLARED VALUE	5		
	CESSIONE DI PIOMBO E CADMIO LEAD AND CADMIUM DISCHARGE - ABGABE VON BLEI UND CADMIUM PERTE DE PLOMB ET CADMIUM - CESIÓN DE PLOMO Y CADMIUM ВЫДЕЛЕНИЕ СВИНЦА И КАДМИЯ - 铅和镉的排放	EN ISO 10545-15	VALORE DICHIARATO DECLARED VALUE	< AL LIMITE DI RILEVAMENTO < THAN INSTRUMENT LIMIT		
	SCIVOLOSITÀ SKID RESISTANCE - RUTSCHWERT GLISSANCE - ADHERENCIA СКОЛЬЗКОСТЬ - 防滑性					
				NAT ST SP ST 20/30mm		
	DM 236/89 BCRA	> 0,40	> 0,40	> 0,40	> 0,40	
	ANSI A326.3	Wet and Dry	≥ 0,42	≥ 0,55	≥ 0,42	≥ 0,55
	AS 4586	-	P2	P5	P2	P5
	DIN 51130	-	R10	R11	R9	R11
	DIN 51097	-	A	A+B+C	A	A+B+C
	UNE 41901	≥ CL1	CL2	CL3	CL1	CL3
	BS 7976 sl.96-4S	Wet and Dry	≥ 0,36	≥ 0,36	≥ 0,36	≥ 0,36
	BS 7976 sl.55-TRL	Wet and Dry	-	≥ 0,36	-	≥ 0,36

Per i certificati specifici, contattare Mirage SpA - For specific certificates, please contact Mirage SpA - Für die speziellen Zertifikate wenden Sie sich bitte an Mirage SpA - Pour les certificats spécifiques, veuillez contacter Mirage SpA
 Para los certificados específicos, contactar Mirage SpA - Для сертификатов обращайтесь в компанию Mirage SpA - 关于具体的证书, 请联系Mirage SpA公司